

Xytron™ M6510A

PPS—(GF+MD)65

65% Glass/Mineral Reinforced, Flame Retardant, Excellent Dimensional Stability

Print Date: 2024-12-10

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES		VALUE	
Molding shrinkage (parallel)	0.3	%	ISO 294-4
Molding shrinkage (normal)	0.5	%	ISO 294-4
MECHANICAL PROPERTIES		VALUE	
Tensile modulus	20000	MPa	ISO 527-1/-2
Tensile modulus (120°C)	11000	MPa	ISO 527-1/-2
Tensile modulus (160°C)	8900	MPa	ISO 527-1/-2
Tensile modulus (180°C)	8000	MPa	ISO 527-1/-2
Tensile modulus (200°C)	7700	MPa	ISO 527-1/-2
Stress at break	145	MPa	ISO 527-1/-2
Stress at break (120°C)	98	MPa	ISO 527-1/-2
Stress at break (160°C)	75	MPa	ISO 527-1/-2
Stress at break (180°C)	70	MPa	ISO 527-1/-2
Stress at break (200°C)	62	MPa	ISO 527-1/-2
Strain at break	1	%	ISO 527-1/-2
Strain at break (120°C)	1.7	%	ISO 527-1/-2
Strain at break (160°C)	2.4	%	ISO 527-1/-2
Strain at break (180°C)	2.5	%	ISO 527-1/-2
Strain at break (200°C)	2.5	%	ISO 527-1/-2
Flexural modulus	20000	MPa	ISO 178
Flexural strength	230	MPa	ISO 178
Flexural modulus (120°C)	14000	MPa	ISO 178
Flexural modulus (160°C)	9100	MPa	ISO 178

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Xytron™ M6510A

Print Date: 2024-12-10

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Flexural modulus (200°C)	7000	MPa	ISO 178
Charpy impact strength (+23°C)	25	kJ/m²	ISO 179/1eU
Charpy impact strength (−30°C)	27	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	6.5	kJ/m²	ISO 179/1eA
Charpy notched impact strength (−30°C)	6.8	kJ/m²	ISO 179/1eA
Rockwell hardness, R scale	120	—	ISO 2039-2
Rockwell hardness, M scale	101	—	ISO 2039-2

THERMAL PROPERTIES	VALUE		
Melting temperature (10°C/min)	280	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	277	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.15	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.27	E-4/°C	ISO 11359-1/-2
Coef. of lin. therm expansion, parallel, above Tg	0.15	E-4/°C	ISO 11359-1/-2
Coef. of lin. therm expansion, normal, above Tg	0.75	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
UL recognition	Yes	—	—
Burning Behav. at 3.0 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	V-0	mm	IEC 60695-11-10
UL recognition	3	—	—
Relative Temperature Index – electrical	130	°C	UL746B
RTI electrical (Thickness (1) tested)	0.7	mm	UL746B
Thermal conductivity in plane	0.7	W/(m K)	ASTM E1461
Thermal conductivity through plane	0.7	W/(m K)	ASTM E1461

ELECTRICAL PROPERTIES	VALUE		
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Electric strength	25	kV/mm	IEC 60243-1

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envallor 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envallor.

Xytron™ M6510A

Print Date: 2024-12-10

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Comparative tracking index	225	V	IEC 60112
Dissipation factor (5GHz)	44	E-4	IEC 61189-2-721
Relative permittivity (5GHz)	5	-	IEC 61189-2-721
OTHER PROPERTIES	VALUE		
Density	1970	kg/m³	ISO 1183

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.